

Technical Data Sheet

Epolight[™] 4148 Near Infrared Dye

DESCRIPTION

Contains palladium

Suitable for plastic applications

Excellent visible light transmission

Excellent light stability

Excellent thermal stability

PROPERTIES

Absorption maximum, λ max: 836 nm


Absorptivity in chloroform: 63 L g⁻¹ cm⁻¹

Appearance: violet powder

Melting point: 273 - 275°C

Solubility in grams/100 grams of solvent:

MEK 1.45 grams Xylene 2.96 grams Cyclohexanone 3.93 grams



Although the information in this data sheet is presented in good faith and believed to be correct, Epolin makes no representations or warranties as to the completeness or accuracy of the information which is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Epolin be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information refers.